



Product Data Sheet

ASPC HBM4265

PRODUCT DESCRIPTION:

HBM4265 is a high density polyethylene, specially developed for large blow molding and jerry cans. This grade offer very good creep strenght, good processability, excellent ESCR and stiffness.

APPLICATIONS:

HBM4265 is recommended for multipurpose blow molding process. This product is suitable for manufacture of small to large jerry cans (eg. Pesticides, surface active liquids etc), also for coextrusion and IBC.

PRODUCT PROPERTIES:

Extruder barrel temperature: 190-220°C

Melt temperature: 205-240°C

Please note that, these processing conditions are recommended by producer only for 100% HBM4265 resin (not in the case of blending with any other compatible material), but because of the many particular factors which are outside our knowledge and control, and may affect the use of product, no warranty is given.

PRODUCT SPECIFICATION:

Properties	Value ⁽¹⁾	unit	Test method
Physical Properties			
Density (23 oC)	942	kg/m3	ISO 1183
MFI (190 oC /21.6Kg)	6.5	dg/min	ISO 1133
Bulk Density	>0.50	g/cm3	ISO 60
Mechanical properties ⁽²⁾			
Tensile Modulus of Elasticity	800	MPa	ISO527
Notched Tensile impact strength(-30 oC)	160	kJ/m2	ISO 8256
ESCR(bottle test)	4000	h	Basell
<i>Additive :Antioxidant – Heat stabilizer</i>			

Notes:

(1) Typical Values: not to be construed as specifications limits.

(2) Properties are based on compression molded sheet using 100% HBM4265.

TOXICITY AND SAFETY:

For more detailed information on handling, storage, safety parameters, refer to relevant SDS of Components.



CONTACT US:

Tehran office: 7th Floor ,No.2551, Kian Tower, (on the corner of Shahid Naseri),
Valiasr AVE, Tehran- Iran

Postal code: 1968643111

P.O.Box:15875-8393

Tel: (+9821) 88645201-7, 85920000

Fax: (+9821) 88645193

www.Aryasasol.com

Email: sop@aspcpe.com

Note: *this information is based on our current knowledge and experience .in view of many factors that may affect processing and application, this data does not relive processors from the responsibility of carrying out their own tests and experiments, neither does it imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.*