



ASPC LFI2119

PRODUCT DESCRIPTION:

LFI2119 is a low density polyethylene, with excellent optical properties. This grade offers a high output and excellent draw down and specially designed for general purpose thin films.

Typical APPLICATIONS:

LFI2119 is recommended for blown film extrusion. This product is suitable for manufacture of general purpose LDPE film packaging and general lamination films.

Typical Data

Properties	Value ⁽¹⁾	unit	Test method
Physical Properties			
MFI (190 °C / 2 .16 Kg)	1.9	dg/min	ISO 1133
Density	921	Kg/m3	ISO 1183 (A)
Mechanical properties ⁽²⁾			
Impact strength	26	KJ/m	ISO 7765-2
Tear strength (TD)	25	KN/m	ISO 6383-2
Tear Strength (MD)	60	KN/m	ISO 6383-2
Yield stress (TD)	11	MPa	ISO 527-1/3
Yield stress (MD)	13	MPa	ISO 527-1/3
Tensile stress at break (TD)	20	MPa	ISO 527-1/3
Tensile stress at break (MD)	35	MPa	ISO 527-1/3
Strain at Break (TD)	>500	%	ISO 527-1/3
Strain at Break (MD)	>150	%	ISO 527-1/3
Modulus of Elasticity (TD)	200	MPa	ISO 527-1/3
Modulus of Elasticity (MD)	190	MPa	ISO 527-1/3
Coefficient of friction	>1		ASTM D 1894
Blocking	20	g	SABTEC method
Re-blocking	100	g	SABTEC method
Optical properties ⁽²⁾			
Haze	9	%	ASTM D 1003A
Gloss (45°)	55	%	ASTM D 2457
Clarity	26	mV	
<i>Additive : Antioxidant</i>			

Notes:

(1) Typical Values: not to be construed as specifications limits.



(2) Properties are based on 25 μm blown film produced at a melt temperature of 170°C and 3 BUR using 100% LFI2119.

General Information

LFI2119 has been manufactured using SABTEC licensed technology.

Processing Conditions:

Extruder temperature profile: 160-185°C

Frost line height: 5-7 times die diameter.

Blow Up Ratio: 2-3

Recommended film thickness: 20 to 50 μm .

Please note that, these processing conditions are recommended by producer only for 100% LFI2119 resin (not in the case of blending with any other compatible material), but because of the many particular factors which are outside our knowledge and control, and may affect the use of product, no warranty is given.

Packaging

Supplied in pellet form and can be packaged in 25kg Bags, one ton semi bulk or 17 tons bulk containers.

Food Packaging

The above-mentioned material meets the relevant requirements as laid down in:

- Regulation 174/2015 (amending Commission Regulation (EU) No. 10/2011)
- European Pharmacopoeia, paragraph 3.1.5.
- Metals test, standard 71-3
- Halogens, IEC 61249-2-21
- Heavy metals, EC Directive 94/62/EC
- RoHS, 2011/65/EU and 2002/96/EC
- Phthalates, Directive 2005/84/EC

Pharmaceutical Application

The above-mentioned grade meets the requirements of the European pharmacopoeia version 6 sections 3.1.5 for pharmaceutical application.

Conveying

Conveying equipment should be designed to prevent accumulation of fines and dust particles can, under certain conditions, pose an explosion hazard. We recommend that the conveying system used:

1. Be equipped with adequate filters.
2. Is operated and maintained in such a manner to ensure no leaks develop.
3. That adequate grounding exists at all times.

We further recommend that good housekeeping will be practiced throughout the facility.

Storage



All resins should be protected from direct sunlight and/or heat during storage. The storage location should also be dry, dust free and the ambient temperature should not exceed 50°C. It is also advisable to process polyethylene resins (in pelletized or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality. ASPC would not give warranty to bad storage conditions, which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is also advisable to process

Polyethylene resins (in pelletized or powder form) within 6 months after delivery, this because also excessive aging of polyethylene can lead to a deterioration in quality.

Handling

Minimal protection to prevent possible mechanical or thermal injury to the eyes. Fabrication areas should be ventilated to carry away fumes or vapors.

Combustibility

Polyethylene resins will burn when supplied adequate heat and oxygen. They should be handled and stored away from contact with direct flames and/or other ignition sources .in burning; polyethylene resins contribute high heat and may generate a dense black smoke. Fires can be extinguished by conventional means with water and mist preferred. In enclosed areas, fire fighters should be provided with self-contained breathing apparatus.

CONTACT US:

Tehran office: 7th Floor, No.2551, Kian Tower, (on the corner of Shahid Naseri), Valiasr AVE, Tehran- Iran

Postal code: 1968643111

P.O.Box:15875-8393

Tel: (+9821) 88645201-7, 85920000

Fax: (+9821) 88645209-10

www. Aryasasol.com

Email: sop@aspcpe.com

Note: this information is based on our current knowledge and experience .in view of many factors that may affect processing and application, this data does not relive processors from the responsibility of carrying out their own tests and experiments, neither does it imply any legally binding assurance of certain properties or of suitability for a specific purpose. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed.

(TEC-PRO-PDS-001- Ver.8 - Date: 05.NOV.2016)